

L.A. ABRASION ASTM C535

Grading 1

After 200 revolutions percent (R200) loss	=	9%
After 1000 total revolutions percent (R1000) loss	=	24%
Ratio R200/R1000	=	0.38

Sample Identification: tan sandstone from Ness Quarry
(contractor sample #2)

Project: Three Springs V1F3
Engineer Technician: G. Jadrych
Project Number: 51689MT
Date: January 12, 2009
Laboratory Number: 1990-A