

## L.A. ABRASION ASTM C535

### Grading 1

After 200 revolutions percent (R200) loss	=	9%
After 1000 total revolutions percent (R1000) loss	=	24%
Ratio R200/R1000	=	0.38

*Sample Identification:* tan sandstone from Ness Quarry  
(contractor sample #2)

Project: Three Springs V1F3  
Engineer Technician: G. Jadrych  
Project Number: 51689MT  
Date: January 12, 2009  
Laboratory Number: 1990-A